



## TECHNICAL DATA SHEET

### 11. SOLVENTS

#### ► Synthetic Solvent D-90

1069 / Version 4 / 04-03-2025



## DESCRIPTION

Thinner specially developed for synthetic paint.

## PROPERTIES

- Characteristic odor and slow evaporation.

## USES

Particularly suitable for paints where its use is recommended as a viscosity regulator, allowing the paint to be diluted and then applied correctly using either a brush, a roller or a paint spray gun. It is also suitable for cleaning all these tools along with the recommended products. Synthetic enamels and varnishes. Primers. Chlorinated rubber paint...

## TECHNICAL DATA

Type	Slow evaporation.
Appearance	Transparent fluid.
Density at 20°C (Kg/L)	0.87 ± 0.05.
Volatile Organic Compounds (COV).	Maximum product content 0,00 g/l,

## HOW TO APPLY

- Please proceed depending on the type of paint to be used.

## SURFACE PREPARATION

### UNPAINTED SURFACES:

New unpainted surfaces:

- Please proceed depending on the type of paint to be used.

### PRE-PAINTED SURFACES IN GOOD CONDITION:

Pre-painted surface in poor condition:

- Please proceed depending on the type of paint to be used.

### PRE-PAINTED SURFACES IN POOR CONDITION:

Pre-painted surface in poor condition:

- Please proceed depending on the type of paint to be used.

## POSSIBLE APPLICATION SYSTEMS

Synthetic Solvent can be applied using a roller, brush or spray gun. Especially indicated for enamel, synthetic varnish, primer, chlorinated rubber, etc.

## SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

## REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.



## 11. SOLVENTS

### ► Synthetic Solvent D-90

1069 / Version 4 / 04-03-2025

## STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 24 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

## LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page [www.isaval.es](http://www.isaval.es). All data in this document are based on laboratory tests conducted at 20°C and 1 atm pressure. Measurements taken "on-site" may vary due to circumstances beyond our control, such as changes in environmental conditions of pressure and temperature.