



TECHNICAL DATA SHEET

1.2 PREPARATION AND FIXING

► Isacrílico Sealing emulsion

Transparent acrylic primer

1131 / Version 5 / 04-12-2023



DESCRIPTION

Fine particle and very penetrating consolidating acrylic aqueous primer and absorption regulator.

PROPERTIES

- High-penetration fine particle, with excellent adherence on porous surfaces
- Consolidating effect for surfaces in poor condition, whitewashed or weathered, after they have been cleaned.
- Resistant to the alkalinity of the surface, such as cement mortars, concrete, brick, etc.
- Water vapour-permeable, allowing transpiration of the support.
- Regularisation of the absorption, improving the adhesion of the subsequent finishing coats.
- Classification pursuant to NF T 36005: Family I Class 7b2
- Interior and exterior application.

USES

Primer coat for paint systems with finishing in aqueous products. Highly recommended for exterior applications in combination with our façade protection products. Indicated for fixing surfaces in bad condition, mineral surfaces and, in general, any porous surface.

TECHNICAL DATA

Appearance	Milky white. Becomes completely transparent when it dries.
Viscosity (Brookfield RVT at 20°C). Poises	5 - 10
Density at 20°C (Kg/L)	1 - 1.1
Yield	Concrete: 30 - 60 m ² /l Mortars: 15 - 20 m ² /l Fibre cement: 15 - 25 m ² /l Plaster/Cast plaster: 10 - 15 m ² /l Painted surfaces: 15 - 40 m ² /l
Drying at 20°C (min)	20 - 30
Second coat	2 h
Brush or roller dilution	Application as a fixer: dilute fixer in water at a ration of 1 (Isacrílico): 4 (water)
Cleaning of utensils and stains	With water before drying.

HOW TO APPLY

- Stir the product until totally smooth.
- The surfaces to be painted must be clean, dry and free of dust, grease, saltpetre, etc.
- If the surface is already painted, ensure the previous paint is in good condition and well-adhered.

SURFACE AND AMBIENT CONDITIONS

AMBIENT TEMPERATURE:

Do not paint at a temperature of below 7°C .

RELATIVE HUMIDITY:

Never apply with relative humidity exceeding 80%.

AMBIENT CONDITIONS:

The paint should not be applied under conditions of excessive sunlight, strong winds, or if rain is forecast.



1.2 PREPARATION AND FIXING

► Isacrílico Sealing emulsion

Transparent acrylic primer

1131 / Version 5 / 04-12-2023

SURFACE PREPARATION

UNPAINTED SURFACES:

Fibre cement:

- Apply one coat of fixer to close the pore and prevent high absorption in the subsequent application of paint.(See possible application systems)

Concrete:

- Elimination of efflorescence and alkalinity by treating with DILUTED ZINC SULPHATE. Regulate absorption by applying a suitable fixer/primer (See possible application systems)

Cement mortar:

- Wait until completely set (min. 30 days).
- Removal of stripping substances

Plaster/Cast plaster:

- Elimination of efflorescence and alkalinity by treating with DILUTED ZINC SULPHATE. Regulate absorption by applying a suitable fixer/primer (See possible application systems)

PRE-PAINTED SURFACES IN GOOD CONDITION:

Pre-painted surface in good condition:

- Regardless of the support to be repainted, its appearance must be homogenised; in other words, adjust the surfaces that are shiny to help to open the pores and foster adhesion. Check the adhesion and resistance of the paint. Correct any texture or planimetry differences that may exist with RHONA repair mortars. Test compatibility between coats.

PRE-PAINTED SURFACES IN POOR CONDITION:

Pre-painted surface in poor condition:

- If the paint is old or badly adhered with defects such as chalking, blistering, peeling, cracking, etc., it must be completely removed and then apply a coat of transparent acrylic fixer. (see possible application systems)

POSSIBLE APPLICATION SYSTEMS

Use a brush or roller for normal application of Isacrílico sealing emulsion. A spray gun may be used, although the former are recommended.

SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local/national legislation.

STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 12 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

1.2 PREPARATION AND FIXING

► Isacrílico Sealing emulsion

Transparent acrylic primer

1131 / Version 5 / 04-12-2023

LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page "www.isaval.es". Data on this Sheet are based on laboratory tests. The measures taken "on site" may vary due to circumstances beyond our control.