



## TECHNICAL DATA SHEET

### 1.2 PREPARATION AND FIXING

#### ► Fixenol Consolidating primer

Siloxane acrylic primer

1138 / Version 5 / 05-12-2023



## DESCRIPTION

Water-based primer based on extremely fine and penetrating acrylic-siloxane copolymers. Enhanced waterproofing effect. Consolidating action on supports of low consistency.

## PROPERTIES

- High-penetration fine particle, with excellent adherence on porous surfaces
- Consolidating effect for surfaces in poor condition, whitewashed or weathered, after they have been cleaned.
- Resistant to the alkalinity of the surface, such as cement mortars, concrete, brick, etc.
- Water vapour-permeable, allowing transpiration of the support.
- Regularisation of the absorption, improving the adhesion of the subsequent finishing coats.
- Effective non-carbonating barrier due to its high resistance to CO<sub>2</sub> diffusion.
- High water-repellent properties, contributing to making the painting process watertight.
- Water-repellent effect.
- Classification pursuant to NF T 36005: Family I Class 10c
- Interior and exterior application.

## USES

Primer for water-based paints, especially indicated for fixing and sealing mineral substrates, even those with low absorption (cement mortar, concrete, Catalan tile, etc.). Highly recommended for use with our Bixolán and Reviflex products for façades. Consolidating action on supports of low consistency prior to the application of the SATE RHONATHERM system.

## TECHNICAL DATA

<b>Appearance</b>	Milky white. Becomes completely transparent when it dries.
<b>Viscosity (Brookfield RVT at 20°C). Poises</b>	5 - 10
<b>Density at 20°C (Kg/L)</b>	1.0 ± 0.05
<b>Content in solids % volume</b>	14 ± 1
<b>Yield</b>	Approximately: Concrete: 15 - 20 m <sup>2</sup> /l Mortars: 10 - 15 m <sup>2</sup> /l Fibre cement: 10 - 15 m <sup>2</sup> /l Plaster/Cast plaster: 5 - 15 m <sup>2</sup> /l Painted surfaces: 15 - 20 m <sup>2</sup> /l
<b>Touch dry</b>	30 min
<b>Second coat</b>	2 - 3 h
<b>Thinner</b>	Do not dilute, ready to use.
<b>Cleaning of utensils and stains</b>	They are cleaned with water before drying.
<b>Volatile Organic Compounds (COV).</b>	Maximum product content 20,10 g/l

## HOW TO APPLY

- The surfaces to be painted must be clean, dry and free of dust, grease, saltpetre, etc.
- If the surface is already painted, ensure the previous paint is in good condition and well-adhered.



## 1.2 PREPARATION AND FIXING

### ► Fixenol Consolidating

#### primer

Siloxane acrylic primer

1138 / Version 5 / 05-12-2023

## SURFACE AND AMBIENT CONDITIONS

### AMBIENT TEMPERATURE:

Do not paint at a temperature of below 7°C .

### RELATIVE HUMIDITY:

Never apply with relative humidity exceeding 80%.

### AMBIENT CONDITIONS:

The paint should not be applied under conditions of excessive sunlight, strong winds, or if rain is forecast.

## SURFACE PREPARATION

### UNPAINTED SURFACES:

#### Concrete:

- Wait until completely set (min. 30 days).
- Removal of stripping substances

#### Fibre cement:

- Eliminate high alkalinity and regulate absorption by applying a suitable fixer/primer (See possible application systems)

#### Plaster/Cast plaster:

- Porous plaster: Apply one coat of suitable fixer to close the pores and prevent high absorption in the subsequent application of paint.

#### Cement mortar:

- Elimination of efflorescence and alkalinity by treating with DILUTED ZINC SULPHATE. Regulate absorption by applying a suitable fixer/primer (See possible application systems)

### PRE-PAINTED SURFACES IN GOOD CONDITION:

#### Pre-painted surface in good condition:

- Regardless of the support to be repainted, its appearance must be homogenised; in other words, adjust the surfaces that are shiny to help to open the pores and foster adhesion. Check the adhesion and resistance of the paint. Correct any texture or planimetry differences that may exist with RHONA repair mortars. Test compatibility between coats.

### PRE-PAINTED SURFACES IN POOR CONDITION:

#### Pre-painted surface in poor condition:

- If the paint is old or badly adhered with defects such as chalking, blistering, peeling, cracking, etc., it must be completely removed and then apply a coat of transparent acrylic fixer. (see possible application systems)

## POSSIBLE APPLICATION SYSTEMS

Use a brush or roller for normal application of Fixenol fixer. A spray gun may be used, although the former are recommended.

## SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

## 1.2 PREPARATION AND FIXING

### ► Fixenol Consolidating

#### primer

Siloxane acrylic primer

1138 / Version 5 / 05-12-2023

## REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local/national legislation.

## STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 12 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

## LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page "www.Isaval.es". Data on this Sheet are based on laboratory tests. The measures taken "on site" may vary due to circumstances beyond our control.