



TECHNICAL DATA SHEET

1.5 ACRYLIC MORTARS



► Reviquarz Primer

Pigmented acrylic primer

1309 / Version 8 / 05-03-2025



DESCRIPTION

Adhesive opaque acrylic primer and absorption regulator for mineral surfaces. Respond all the requirements established in the "GREEN BUILDING", offering the highest possible score for BREEAM and / or LEED certifications.

PROPERTIES

- High-penetration thin particle, with excellent adherence on porous supports.
- Resistant to the alkalinity of the surface, such as cement mortars, concrete, brick, etc.
- Water vapour-permeable, allowing transpiration of the support.
- Regularisation of the absorption, improving the adhesion of the subsequent finishing coats.
- Effective non-carbonating barrier due to its high resistance to CO2 diffusion.
- Improves the opacity of subsequent layers.
- Interior and exterior application.
- With anti-mould paint preservative for film, avoids the appearance of fungus and algae spots on its surface.
- This product has a last generation biocidal film preservative against the proliferation of microorganisms on the coating that offers long-lasting protection, although limited in time. The duration will depend on the atmospheric conditions and the concentration of spores of the place, and for this reason the proliferation of fungi and algae cannot be definitively avoided. If the architectural design of the building does not provide sufficient protection for the façade and the environmental conditions are conducive to the development of microorganisms, it is suggested to carry out periodic preventive maintenance on the affected surface.

USES

Primer coat for paint systems with finishing in aqueous products. Highly recommended for exterior applications in combination with our façade protection products. Indicated for fixing mineral surfaces and, in general, any porous surface.

TECHNICAL DATA

Appearance	Matt.
Colour	White and colours from the Esencia and Coloritud charts.
Viscosity (Brookfield RVT at 20°C). Poises	90 - 110
Density at 20°C (Kg/L)	1.40 + 0.05
Touch dry	30 min
Second coat	4 - 6 h
% brush or roller dilution	0 - 15
Cleaning of utensils and stains	With water before drying.
Volatile Organic Compounds (COV).	Maximum product content 0,10 g/l
Usage	ETICS: 0.27 - 0.32 l/m2

HOW TO APPLY

- Stir the product until totally smooth.
- The surfaces to be painted must be clean, dry and free of dust, grease, saltpetre, etc.
- If not, the surface must be cleaned properly and prepared with a coat of appropriate fixer.
- If the surface is already painted, ensure the previous paint is in good condition and well-adhered.



1.5 ACRYLIC MORTARS

► Reviquarz Primer

Pigmented acrylic primer

1309 / Version 8 / 05-03-2025

SURFACE AND AMBIENT CONDITIONS

AMBIENT TEMPERATURE:

Do not paint at a temperature of below 7°C .

RELATIVE HUMIDITY:

Never apply with relative humidity exceeding 80%.

AMBIENT CONDITIONS:

The paint should not be applied under conditions of excessive sunlight, strong winds, or if rain is forecast.

SURFACE PREPARATION

UNPAINTED SURFACES:

Plaster/Cast plaster:

- Apply one coat of fixer to close the pore and prevent high absorption in the subsequent application of paint.(See possible application systems)

Cement mortar:

- Elimination of efflorescence and alkalinity by treating with DILUTED ZINC SULPHATE. Regulate absorption by applying a suitable fixer/primer (See possible application systems)

Fibre cement:

- Eliminate high alkalinity and regulate absorption by applying a suitable fixer/primer (See possible application systems)

Concrete:

- Wait until completely set (min. 30 days).
- Removal of stripping substances

PRE-PAINTED SURFACES IN GOOD CONDITION:

Pre-painted surface in good condition:

- Regardless of the support to be repainted, its appearance must be homogenised; in other words, adjust the surfaces that are shiny to help to open the pores and foster adhesion. Check the adhesion and resistance of the paint. Correct any texture or planimetry differences that may exist with RHONA repair mortars. Test compatibility between coats.

PRE-PAINTED SURFACES IN POOR CONDITION:

Pre-painted surface in poor condition:

- If the paint is old or badly adhered with defects such as chalking, blistering, peeling, cracking, etc., it must be completely removed and then apply a coat of transparent acrylic fixer. (see possible application systems)

POSSIBLE APPLICATION SYSTEMS

Is normally applied using a brush or roller, or a spray gun. The perfect coverage, waterproofing, and protection of surfaces are recommended with two coats. The 1st coat is advisable to dilute by 15% to 20% with drinking water. The 2nd coat is applied pure or diluted by 5-10%.

SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.

TECHNICAL DATA SHEET

1.5 ACRYLIC MORTARS

► Reviquarz Primer

Pigmented acrylic primer

1309 / Version 8 / 05-03-2025

STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 12 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page www.isaval.es. All data in this document are based on laboratory tests conducted at 20°C and 1 atm pressure. Measurements taken "on-site" may vary due to circumstances beyond our control, such as changes in environmental conditions of pressure and temperature.