TECHNICAL DATA SHEET

7. HIGH-END DECORATION

▶ Venetian stucco

Synthetic stucco

1371 / Version 3 / 06-03-2026

DESCRIPTION

Stucco for interior decoration by giving a “marmorino” effect through the technique of using the spatula.

PROPERTIES

- Great hardness and resistance.
- Can imitate the appearance of marble on the surface to which it has been applied.
- Provides warm surfaces.

USES

This product is used in high-end decoration to obtain the beautiful effects of marble veins on walls and ceilings of entrance areas and domestic or commercial accommodation rooms. When a luxury finish is desired on plaster or cast finishes. Exclusively for interior use. STUCCO is not washable.

TECHNICAL DATA

Finish	Smooth, polished and shiny.
Colour	Neutral base and colour chart.
Density at 20ºC (Kg/L)	1.6 ± 0.05
Consumption (Kg/m2)	0.6 - 1
Touch dry	60 min Dry spatulas (gloss): 30 min
Can be sanded (hours)	24
Cleaning of utensils and stains	With water
Volatile Organic Compounds (COV).	Maximum product content 30,00 g/l

HOW TO APPLY

- Stir the product until totally smooth.
- The surfaces to be painted must be clean, dry and free of dust, grease, saltpetre, etc.

SURFACE AND AMBIENT CONDITIONS

AMBIENT TEMPERATURE:

Apply at temperatures higher than 10ºC.

RELATIVE HUMIDITY:

Never apply with relative humidity of less than 85%.

C/ Velluters, Parcela 2-14 · Pol. Ind. Casanova · 46394, Ribarroja del Turia · Valencia - España
+34 96 164 00 01 +34 96 164 00 02 isaval@isaval.es

▶ Venetian stucco

Synthetic stucco

1371 / Version 3 / 06-03-2026

SURFACE PREPARATION

UNPAINTED SURFACES:

New unpainted surfaces:

- Regardless of the support to be repainted, its appearance must be homogenised; in other words, adjust the surfaces that are shiny to help to open the pores and foster adhesion. Check the adhesion and resistance of the paint.Correct any texture or planimetry differences that may exist with RHONA repair mortars. Test compatibility between coats.
- Remove efflorescences, product residues and foreign substances (grease, dust, oils and/or derivatives, etc.).
- Regulate high porosity by applying a coat of fixer (See possible application systems).

PRE-PAINTED SURFACES IN POOR CONDITION:

Pre-painted surface in poor condition:

- If the paint is old or badly adhered with defects such as chalking, blistering, peeling, cracking, etc., it must be completely removed and then apply a coat of transparent acrylic fixer. (see possible application systems)
- Regardless of the support to be repainted, its appearance must be homogenised; in other words, adjust the surfaces that are shiny to help to open the pores and foster adhesion. Check the adhesion and resistance of the paint.Correct any texture or planimetry differences that may exist with RHONA repair mortars. Test compatibility between coats.

POSSIBLE APPLICATION SYSTEMS

Use a trowel for normal application of Venetian stucco. Prior to the top coat and depending on the wall apply primer suitable for the yield specified in each case. Use a trowel to apply one or more coats of the product to the prepared surface until even colour and thickness are achieved. It can also be applied using a wool roller and diluting with 5% water. After 24 hours, sand with fine sandpaper and remove the resulting dust with a cloth. With a stainless steel spatula, apply very thin coats of the product at equidistant spaces. After approximately 30 minutes, rub with the stainless steel spatula to bring out the shine. In the spaces previously not applied with a spatula, repeat the application and polishing.

PRIMERS:

- Fixenol Pigmented: non-homogeneous surfaces (various materials, areas with different colours, repairs, etc.), where FIXENOL PIGMENTED is to be applied in the desired colour, in order to regularise the colour, absorption and appearance of the surface.Yield: 8 - 15 m2/L. Coats: 1

FINISH ESTUCO VENECIANO:

- Yield: 0,6 - 1 kg/m2
- Coats: 2 - 3

SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.

STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 12 months from manufacture in fully sealed original container, indoors and at temperatures between 5º and 35º C.

C/ Velluters, Parcela 2-14 · Pol. Ind. Casanova · 46394, Ribarroja del Turia · Valencia - España
+34 96 164 00 01 +34 96 164 00 02 isaval@isaval.es

▶ Venetian stucco

Synthetic stucco

1371 / Version 3 / 06-03-2026

LEGAL TEXT NOTE

This information, particularly the recommendations regarding the application and end use of the product, is given in good faith, based on Pinturas Isaval´s current knowledge and experience with the products when correctly stored, handled, and applied under normal conditions within their shelf life and in accordance with Pinturas Isaval's recommendations. In practice, the potential differences in materials, substrates, and actual conditions at the application site are such that no warranty of merchantability or fitness for a particular purpose, nor any obligation, may be inferred from the information in this document or from any other written recommendation or advice given. The user must conduct their own tests to verify the product's suitability for the intended use. Pinturas Isaval reserves the right to modify the properties of its products. Third-party property rights must be respected. All orders are accepted under the terms of our current General Conditions of Sale and Supply. Users must consult and use the most recent and updated version of the local Product Data Sheets, which can be sent upon request or found on the website www.Isaval.es. The data provided are indicative and not legally binding, based on laboratory tests performed at 20°C and 1 atm pressure. On-site measurements may vary due to circumstances beyond our control, such as changes in environmental pressure and temperature. The reported ranges are based on historical measurements. The product must not be used for purposes other than those specified. If further clarification on product characteristics or usage is needed, users should contact PINTURAS ISAVAL S.L. staff.

C/ Velluters, Parcela 2-14 · Pol. Ind. Casanova · 46394, Ribarroja del Turia · Valencia - España

+34 96 164 00 01 **+34 96 164 00 02** **isaval@isaval.es**