TECHNICAL DATA SHEET

7. HIGH-END DECORATION

▶ Travertin stucco

Lime-based decorative stucco

2206 / Version 5 / 10-04-2025

DESCRIPTION

Decorative stucco based on powdered lime, which achieves an effect similar to the ancient Roman TRAVERTINE marble.

PROPERTIES

- High breathability.
- Excellent behaviour against the formation of mould and proliferation of bacteria on the surface.
- Interior/exterior use.

USES

This product is used in high-end decoration to obtain the beautiful effects of travertine marble veins on walls and ceilings of entrance areas and domestic or commercial accommodation rooms. Ideal on outdoor façades of villas and historic buildings. The product can be applied on brick, concrete or any standard absorbent or semi-absorbent surface in construction.

TECHNICAL DATA

Colour	White.
Density at 20ºC (Kg/L)	1.7 ± 0.05
pH	12.5 - 13.5
% Mixing water	30 - 35
Usage	1.6 Kg/m2/mm
Touch dry (hours)	3
Can be sanded (hours)	24
Cleaning of utensils and stains	With water immediately after use. If the product hardens, it can only be removed mechanically.

HOW TO APPLY

- The surface must be intact, clean, consistent and free from dust, grease, oil, micro-organisms and any other material that could affect the products correct adhesion to the surface.
- If there is any kind of anomaly on the surface, the relevant cleaning and repair processes must be carried out (dust removal, cleaning processes and masonry repairs) and any loose or falling parts removed in order to ensure the above-mentioned conditions.
- Do not wet the surfaces before applying the putty.

SURFACE PREPARATION

UNPAINTED SURFACES:

New unpainted surfaces:

- Paint one or two coats of primer diluted with 5-10% water with a brush or roller.
- Apply a first coat of product with a stainless steel spatula, completely smoothing the surface. The thickness of this first coat should be 2-3 mm as it serves as a smoothing coat on the surface.
- To achieve the scraped effect, once the second coat has been applied and once the product has hardened on the surface but has not dried, scrape the surface horizontally from right to left with the cutting edge of the stainless steel trowel. Next, gently smooth with a trowel, thus obtaining the scraped areas characteristic of travertine marble.Once completely dry, colour and protect with travertine stucco glaze.

C/ Velluters, Parcela 2-14 · Pol. Ind. Casanova · 46394, Ribarroja del Turia · Valencia - España
+34 96 164 00 01 +34 96 164 00 02 isaval@isaval.es

▶ Travertin stucco

Lime-based decorative stucco

2206 / Version 5 / 10-04-2025

POSSIBLE APPLICATION SYSTEMS

Normal application is performed by trowel.
1st COAT: Apply a first coat of ESTUCO TRAVERTINO with a stainless steel spatula, completely smoothing the surface. The thickness of this first coat should be 2-3 mm as it serves as a smoothing layer for the surface.
STRIPED EFFECT
Once the second coat has been applied, when the product has hardened superficially but has not dried, scrape the surface horizontally from right to left with the cutting edge of the stainless steel trowel.
Subsequently, smooth with the trowel gently, thus obtaining the scratched areas characteristic of travertine marble.
After complete drying color and protect with TRAVERTINO STUCCO SAIL.

FINISH ESTUCO TRAVERTINO:

- Yield: 1.6 - 1.7 Kg/ m2/mm
- Coats: 2

SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.

STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 12 months from manufacture in fully sealed original container, indoors and at temperatures between 5º and 35º C.

LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page www.Isaval.es. All data in this document are based on laboratory tests conducted at 20°C and 1 atm pressure. Measurements taken "on-site" may vary due to circumstances beyond our control, such as changes in environmental conditions of pressure and temperature.

C/ Velluters, Parcela 2-14 · Pol. Ind. Casanova · 46394, Ribarroja del Turia · Valencia - España
+34 96 164 00 01 **+34 96 164 00 02** **isaval@isaval.es**