



TECHNICAL DATA SHEET

9.2 SOLVENT BASED

► Chlorinated rubber floors Glossy

Pigmented chlorinated rubber paint

2353 / Version 2 / 04-03-2025



DESCRIPTION

Paint based on chlorinated rubber resins especially indicated for protecting and decorating floors.

PROPERTIES

- Good adhesion on concrete, cement and similar.
- Low resistance to diesel, brake fluid and lubricating oil.
- Quick drying.
- Good hardness, resistance to abrasion and shock.
- Good brushability.

USES

Developed for applying to: floors of car parks, industrial buildings and places where floor protection and decoration is required.

TECHNICAL DATA

Appearance	Gloss.
Colour	green, grey, red and colours from RAL catalogue.
Viscosity (Brookfield RVT at 20°C). Poises	40 - 70
Density at 20°C (Kg/L)	1.2 - 1.4
Content in solids % volume	46 - 50
Adhesion to cement mortar substrate (MPa)	2.02
Adhesion to concrete substrate (MPa)	2.24
Yield (m²/L):	6 - 10
Touch dry (20°C) (min)	30
Second coat (hours)	6
Thinner	D-40
% brush or roller dilution	0 - 5
% spray gun dilution	0 - 5
Volatile Organic Compounds (COV).	Maximum product content 498 g/l

HOW TO APPLY

- Stir the product until totally smooth.
- The surfaces to be painted must be clean, dry and free of dust, grease, saltpetre, etc.
- If the surface is already painted, ensure the previous paint is in good condition and well-adhered.

SURFACE AND AMBIENT CONDITIONS

AMBIENT TEMPERATURE:

Do not paint at below 10°C or above 40°C.

RELATIVE HUMIDITY:

Never apply with relative humidity exceeding 80%.

AMBIENT CONDITIONS:

The paint should not be applied under conditions of excessive sunlight, strong winds, or if rain is forecast.

9.2 SOLVENT BASED

► Chlorinated rubber floors

Glossy

Pigmented chlorinated rubber paint

2353 / Version 2 / 04-03-2025

SURFACE PREPARATION

UNPAINTED SURFACES:

Asphalt agglomerates:

- Removal of product residues and foreign substances.
- Test in advance if there is the possibility of any bleeding.

Concrete:

- The paving must be in the very best condition as regards optimum preparation, i.e. clean, dry and even. Wait to complete setting (1 month).
- Remove efflorescences, product residues and foreign substances (grease, dust, oils and/or derivatives, etc.).
- Regulate high porosity by applying a coat of fixer (See possible application systems).
- It is essential to regulate porosity on the surface to ensure penetration and anchorage of the paint; to achieve this, the best outcomes are obtained using mechanical methods, which remove any type of unwanted substance or foreign body and regulate surface porosity.
- If mechanical treatment cannot be carried out, use at least one chemical treatment: remove foreign or undesired agents using diluted hydrochloric acid, then remove the acid residues with plenty of water. Allow the surface to dry and then paint as normal.
- Apply one coat of fixer to close the pore and prevent high absorption in the subsequent application of paint.(See possible application systems)

PRE-PAINTED SURFACES IN POOR CONDITION:

Pre-painted surface in poor condition:

- If the surface is in poor condition or flaking, poorly adhered residues must be removed using chemical or mechanical stripping
- Clear oil or grease residue.
- See compatibility with the previous paint.
- Apply one coat of fixer to close the pore and prevent high absorption in the subsequent application of paint.(See possible application systems)

POSSIBLE APPLICATION SYSTEMS

Use a roller or spray gun for normal application of chlorinated rubber floor gloss. Prior to the top coat and depending on the wall apply primer suitable for the yield specified in each case.

PRIMERS:

- Fixacril Solvent-based acrylic fixer: Non-consolidated absorbent surfaces:Yield:Concrete: 15-20 m2/L.Cement mortars: 10-15 m2/L.Fibre cement: 10 - 15 m2/L.Plaster/Cast plaster: 5 - 15 m2/L.Painted surfaces: 15 - 20 m2/L. Coats: 1

FINISH CLOROCAUCHO SUELOS (BRILLO):

- Yield: 6 - 10 m2/l
- Coats: 1

SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.

9.2 SOLVENT BASED

► Chlorinated rubber floors

Glossy

Pigmented chlorinated rubber paint

2353 / Version 2 / 04-03-2025

STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 24 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page www.isaval.es. All data in this document are based on laboratory tests conducted at 20°C and 1 atm pressure. Measurements taken "on-site" may vary due to circumstances beyond our control, such as changes in environmental conditions of pressure and temperature.