



## TECHNICAL DATA SHEET

### 1.2 PREPARATION AND FIXING

#### ► Rhona A-250 Rough

Opaque and textured primer

2449 / Version 3 / 05-03-2025



## DESCRIPTION

Opaque and textured acrylic primer, which acts as a physical-chemical adhesion promoter and absorption regulator for mineral substrates.

## PROPERTIES

- Resistant to the alkalinity of the surface, such as cement mortars, concrete, brick, etc.
- Water vapour-permeable, allowing transpiration of the support.
- Regularisation of the absorption, improving the adhesion of the subsequent finishing coats.
- Effective non-carbonating barrier due to its high resistance to CO<sub>2</sub> diffusion.
- Improves the opacity of subsequent layers.
- Interior and exterior application.
- Its textured appearance may conceal minor surface defects.

## USES

Primer coat for painting systems with finishing in aqueous products, being highly recommended in outdoor uses in combination with our high thickness façade protection products. Also used as a connecting bridge between supports that are difficult to anchor and mortars.

## TECHNICAL DATA

<b>Appearance</b>	Matt, rough texture.
<b>Colour</b>	White.
<b>Viscosity (Brookfield RVT at 20°C). Poises</b>	140 - 160
<b>Density at 20°C (Kg/L)</b>	1.55 + 0.05.
<b>Yield</b>	8 - 15 m <sup>2</sup> /l. Highly variable depending on the area to which it is applied.
<b>Touch dry</b>	20 min
<b>Second coat</b>	2 h
<b>Cleaning of utensils and stains</b>	With water before drying.
<b>Volatile Organic Compounds (COV).</b>	Maximum product content 0,10 g/l

## HOW TO APPLY

- Stir the product until totally smooth.
- The surfaces to be painted must be clean, dry and free of dust, grease, saltpetre, etc.
- If not, the surface must be cleaned properly and prepared with a coat of appropriate fixer.
- If the surface is already painted, ensure the previous paint is in good condition and well-adhered.

## SURFACE AND AMBIENT CONDITIONS

### AMBIENT TEMPERATURE:

Do not paint at a temperature of below 7°C.

### RELATIVE HUMIDITY:

Never apply with relative humidity exceeding 80%.

### AMBIENT CONDITIONS:

The paint should not be applied under conditions of excessive sunlight, strong winds, or if rain is forecast.



## 1.2 PREPARATION AND FIXING

### ► Rhona A-250 Rough

Opaque and textured primer

2449 / Version 3 / 05-03-2025

## SURFACE PREPARATION

### UNPAINTED SURFACES:

#### Plaster/Cast plaster:

- Apply one coat of fixer to close the pore and prevent high absorption in the subsequent application of paint. (See possible application systems)

#### Fibre cement:

- Eliminate high alkalinity and regulate absorption by applying a suitable fixer/primer (See possible application systems)

#### Cement mortar:

- Elimination of efflorescence and alkalinity by treating with DILUTED ZINC SULPHATE. Regulate absorption by applying a suitable fixer/primer (See possible application systems)

#### Concrete:

- Wait until completely set (min. 30 days).
- Removal of stripping substances

### PRE-PAINTED SURFACES IN GOOD CONDITION:

#### Pre-painted surface in good condition:

- Regardless of the support to be repainted, its appearance must be homogenised; in other words, adjust the surfaces that are shiny to help to open the pores and foster adhesion. Check the adhesion and resistance of the paint. Correct any texture or planimetry differences that may exist with RHONA repair mortars. Test compatibility between coats.

### PRE-PAINTED SURFACES IN POOR CONDITION:

#### Pre-painted surface in poor condition:

- If the paint is old or badly adhered with defects such as chalking, blistering, peeling, cracking, etc., it must be completely removed and then apply a coat of transparent acrylic fixer. (see possible application systems)

## POSSIBLE APPLICATION SYSTEMS

The normal application of RHONA A-250 can be done by brush or roller, it is not ruled out by spray gun.

### FINISH RHONA A-250 RUGOSO:

- Yield: 8 - 15 m<sup>2</sup>/l
- Coats: 2

## SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

## REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.

## STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 12 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

## 1.2 PREPARATION AND FIXING

### ► Rhona A-250 Rough

Opaque and textured primer

2449 / Version 3 / 05-03-2025

## LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page [www.isaval.es](http://www.isaval.es). All data in this document are based on laboratory tests conducted at 20°C and 1 atm pressure. Measurements taken "on-site" may vary due to circumstances beyond our control, such as changes in environmental conditions of pressure and temperature.