



TECHNICAL DATA SHEET

3.1 SOLVENT BASED

► Enamel PU Basic

Industrial polyurethane enamel for indoor.

2510 / Version 3 / 16-01-2024



DESCRIPTION

Two-component industrial polyurethane enamel indicated for use on metal surfaces for indoor.

PROPERTIES

- Suitable for aggressive environment such as industrial and marine areas.
- High opacity and levelling.
- Good adhesion on difficult surfaces.
- Resistant to shock and abrasion.
- For interior use

USES

Especially designed for painting a wide variety of surfaces, both metal (iron, steel, galvanised, brass, aluminium, etc.) and non-metallic (wood, concrete, plaster, etc.).

TECHNICAL DATA

Appearance	Glossy.
Colour	Colours from RAL chart.
Density at 20°C (Kg/L)	1.25 a 1.40.
Content in solids % volume	50 - 53.
Mixing ratio	4:1 by volume, with HARDENDER for ESMALTE PU BASIC.
Useful life of mixture	2 - 3 h
Gloss (UNE EN ISO 2813)	90% at 60°
Yield	10 - 13 m ² /l (40 - 50 microns dry)
Total cure at 20°C (days)	8
Touch dry	2 h
Second coat	minimum 12 h
Thinner	D-30.
% brush or roller dilution	0 - 5
% spray gun dilution	5 - 10

HOW TO APPLY

- Stir the product until totally smooth.
- The surfaces to be painted should be consistent, without any poorly adhered materials and be clean, dry, free of dust, grease, saltpetre, mould, fungus or algae.
- Check the compatibility with the previous paint



3.1 SOLVENT BASED

► Enamel PU Basic

Industrial polyurethane enamel for indoor.

2510 / Version 3 / 16-01-2024

SURFACE AND AMBIENT CONDITIONS

AMBIENT TEMPERATURE:

Do not paint at a temperature of below 10°C .

SURFACE TEMPERATURE:

It should be 2 - 3 °C above dew point when painting.

RELATIVE HUMIDITY:

Never apply with relative humidity exceeding 80%.

AMBIENT CONDITIONS:

The paint should not be applied under conditions of excessive sunlight, strong winds, or if rain is forecast.

3.1 SOLVENT BASED

► Enamel PU Basic

Industrial polyurethane enamel for indoor.

2510 / Version 3 / 16-01-2024

SURFACE PREPARATION

UNPAINTED SURFACES:

Iron and Steel:

- Remove any existing mill scale. Get rid of any remains of rust or already rusted material (sand blasting or by scraping and mechanical or manual brushing, see possibility of application of our rust converter if necessary), until the surface is free of rust. Apply 1 or 2 coats of anti-rust primer according to instructions given in the possible application systems.
- It is advisable to apply an anti-rust primer for utmost protection of metal surfaces. (See possible application systems)
- Paint using the normal procedure.

Concrete:

- Eliminate high alkalinity and regulate absorption by applying a suitable fixer/primer (See possible application systems)
- Paint using the normal procedure.

Wood:

- Removal of product residues and foreign substances.
- Sand and apply one or two coats of primer and leave to dry for a minimum of 48 hours.
- Paint using the normal procedure.

Non-ferrous metals:

- Removal of product residues and foreign substances.
- Paint using the normal procedure.

PRE-PAINTED SURFACES IN POOR CONDITION:

Concrete:

- Elimination of efflorescence and alkalinity by treating with DILUTED ZINC SULPHATE. Regulate absorption by applying a suitable fixer/primer (See possible application systems)
- Paint using the normal procedure.

Iron and Steel:

- If the enamel-coated surface is not in ideal condition, the existing enamel layer should be removed with PAINT STRIPPER.
- Remove any existing mill scale. Get rid of any remains of rust or already rusted material (sand blasting or by scraping and mechanical or manual brushing, see possibility of application of our rust converter if necessary), until the surface is free of rust. Apply 1 or 2 coats of anti-rust primer according to instructions given in the possible application systems.
- Paint using the normal procedure.

Wood:

- If the enamel-coated surface is not in ideal condition, the existing enamel layer should be removed with PAINT STRIPPER.
- Removal of product residues and foreign substances.
- Sand and apply one or two coats of primer and leave to dry for a minimum of 48 hours.
- Paint using the normal procedure.

3.1 SOLVENT BASED

► Enamel PU Basic

Industrial polyurethane enamel for indoor.

2510 / Version 3 / 16-01-2024

POSSIBLE APPLICATION SYSTEMS

Use a brush, roller or spray gun for normal application of Aliphatic enamel Pu basic gloss. At least two top coats are recommended. The recommended thickness is 40-50 microns dry. Prior to the top coat and depending on the wall apply primer suitable for the yield specified in each case.

PRIMERS:

- Imprex HS: anti-rust epoxy primer with high solids. Yield: 6 - 10 m²/L. Microns: 100
- Imprex Two-component epoxy primer: anti-rust epoxy primer. Yield: 10 - 12 m²/L Microns: 40 - 50
- Imprex RZ: anti-rust epoxy primer for highly corrosive environments. Yield: 11 - 14 m²/L Microns: 50
- Isalnox Multi-adhesive Primer: protection of rust-free metallic surfaces (steel, galvanised steel, aluminium, etc.), sealant for non-metallic surfaces (wood, gypsum, PVC, etc.) Yield: 10 - 12 m²/L. Coats: 1
- Imprex MIO: anti-rust epoxy primer for highly corrosive environments. Yield: 10 - 14 m²/L Microns: 60
- Shop Primer: Modified vinyl primer with phosphating and passivating one-component effect for industrial use. Yield: 15/20 m² / l in thicknesses of 10-15 microns.
- Improxy HS Primer: high solids anti-corrosion synthetic primer with ultra-fast drying for the temporary maintenance of metal structures. Coverage: 4 -8 m² / L in thicknesses of 40-50 microns.

FINISH ESMALTE PU BASIC:

- Yield: 10 - 13 m²/l
- Coats: 2

SAFETY

Consult the current safety data sheet for safe handling (Section 8.2). Unsuitable for children. Keep out of the reach of children. Do not place painted surfaces into the mouth.

REMOVAL

Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling, in line with the local and national legislation in force. Take the necessary measures to ensure waste is kept to an absolute minimum. Analyse all possible methods for reuse or recycling. Do not pour down drains or into the environment. Dispose of the product at an authorised waste disposal site or through an authorised waste management company. Waste must be handled, stored and disposed of pursuant to current local- national legislation.

STORAGE

See storage conditions indicated in section 7.2 of the current safety data sheet. Store the containers away from high temperatures, direct exposure to the sun and frost. Maximum recommended storage time: 24 months from manufacture in fully sealed original container, indoors and at temperatures between 5° and 35° C.

LEGAL TEXT NOTE

This information and, in particular, the recommendations regarding the application and final use of the product, are given in good faith, based on the current knowledge and experience of Isaval Paints of the products when they are properly stored, handled and applied, in normal situations, within its useful life, according to the recommendations of Pinturas Isaval. In practice, the possible differences in the materials, supports and actual conditions at the place of application are such that it cannot be inferred from the information in this document, no any other written recommendation, neither any advice offered, will insure the guarantee in terms of marketing or suitability for particular purposes, neither any obligation outside of any legal relationship that may exist. The user of the products must carry out the tests to verify their suitability according to the use they want to give. Pinturas Isaval reserves the right to change the specifications of its products. The property rights of third parties must be respected. All orders are accepted according to the terms of our current General Conditions of Sale and Supply. Users should know and use the latest and updated version of the local Product Data Sheets, a copy of which will be sent to whoever requests them, or can also be obtained on the page "www.isaval.es". Data on this Sheet are based on laboratory tests. The measures taken "on site" may vary due to circumstances beyond our control.